







TANKING SLURRY

Waterproof Cement Based Coating

Technical Data Sheet



CLASS **EN998-1**

LEVELMASTER RANGE

Description:

A cementitious waterproof coating designed for use below and above ground for cellars, retaining walls, and tanks. Conforms to EN998-1:2016.

Features & Benefits:

- Excellent adhesion to most common building materials see surface preparation.
- Water based safe to apply on damp surfaces.
- Easy application applied by brush.
- Resistant to positive and negative water pressure up to 7 Bar.
- WRAS approved.

Uses

High performance; high water resistance (EN 998-1), flexibility, good adhesion and set control in a water mix form. Bond It TANKING SLURRY is a blend of Portland cements, quality graded aggregates and chemical modifiers, which provide a waterproof coating system.

Suitable Applications: Tanks, pits and swimming pools; Above and below ground walls and floors; Cellars, underground rooms; Interior spaces, e.g. ducting, party walls, lift shafts; Fish ponds.

Limitations

Do not apply over plaster, wallpaper or paint as the dampness will be retained under the Bond It TANKING SLURRY and cause the plaster, wallpaper or paint to fail taking all subsequent coatings along with it. Not suitable for wood, plastic or fabric. Not suitable for Gypsum based plasters. Stainless steel form details only to be used.

Preparation

- 1. Suitable for use with; brick, stone, and concrete surfaces.
- 2. It is recommended sources of water and damp are removed. A damp proof course should be employed.
- 3. All contact surfaces must be clean and sound, and free from dust, grease particles and loose material or previous coatings. The surface must be prepared using abrasive tools, jet washing or wire brushing and any debris removed with clean water. A sound mechanical key surface must be achieved prior to slurry or backing render application, otherwise damp will build up under the tanking coating and will affect the bond to the substrate.
- 4. Tap off water pressure where necessary insert a fillet at floor and wall joint.
- 5.Running water and surface defects, such as holes, cracks or fractures should be filled with Bond It PLUG IT. PLUG IT can be over coated with TANKING SLURRY as soon as it is cool and dry to the touch.
- 6. Under normal applications no priming is required. For difficult surfaces Bond It EXTERIOR PREGRIT or SBR ADMIXTURE may be

applied as a primer coat.

7. Seal around all services and pipes with Bond It GRIPBOND PRO HYBRID SEALANT.



Mixing

- 1. The water requirement to produce the coating is 5 Litres of clean water per 20Kg of dry material.
- 2. Pour the required quantity of water into suitable mixing bucket / container. Slowly add the powder to the water whilst continuously mixing with a mechanical paddle / stirrer.
- 3. Mixing should be continued until all the powder is homogenously combined into a "creamy" consistency. As a rule of thumb when the block brush is placed into the mix bristles first the non bristle part should float on the surface when the correct consistency is achieved.
- 4. Additional water will reduce the effectiveness of the product.
- 5. Do not mix more product than can be applied in a 30 minute period.

Application

Bond It TANKING SLURRY can be applied when both the surface and air temperature is in the range of +5°C to +25°C. This product is susceptible to frost damage – see storage. Dampen the surface, ensure no standing or pooled water is present. This is a two coat application. Apply the first coat to a thickness of 2mm in a vertical direction, working the slurry into any pinholes, crevices or edges thoroughly with a brush. Rollers can be used over larger sections but the surface should be inspected for any gaps or breaks in coating. The slurry needs to be a continuous film for it to be effective, this is especially important at the floor/wall junction. Inspect the coating after approximately 3 hours for breaks or gaps. If the film is consistent, touch dry and fully adhered apply a second coat horizontally, as this will ensure complete coverage of the substrate. Do not re-temper stiffened material. Once applied protect from frost, direct sunlight and wet weather.

Curing

Drying times are affected by the substrate, the moisture content of the substrate, the temperature of the substrate and the air. Under standard conditions the film should be touch dry in 2 hours and thoroughly dry in 6-8 hours. Good ventilation is essential for

correct drying and curing of the product. Dehumidifiers or other heat sources to accelerate drying must not be used. Protect from frost, direct sunlight, and drying winds for 24 hours. Note: TANKING SLURRY is not designed to be a final wearing coat.

Overcoating

It is recommended that Bond It TANKING SLURRY is not over coated until after 5 days. If plastering, only a cement based renovating plaster can be used. Solvent based paints are not suitable. Water based paints can be used however, the first coat should be of a matt emulsion type, not silk or similar.

Cleaning

Clean tools immediately after use in warm, soapy water then rinse in clean water.

20kg paper sack.

Coverage

One 20Kg bag is sufficient to cover approximately 12m².

Specification Summary

Application Temperature

WRAS Certificate Number

Product / Order Details

Colour

Grev

Grey

Full Curing Time

Commodiry Code

Colour

Grey powder.

Appearance

Composition

Coverage

Pot Life

Skin Time

Code

BDH107

BDH107T

Shelf Life

12 months from date of manufacture, before the date shown on the bag when stored in unopened sacks.

Storage Conditions

Store in original unopened bags. Once opened the product will absorb moisture from the air and become unusable. Store in a cool, dry place between +5 to +25°C and protect from frost. Do not place bags on the ground.

Disposal Of Containers

Do not leave empty containers where residue could be harmful to children, animals or the environment. Remove any bags or used material to a central disposal point in accordance with local regulations.

Health & Safety

Please refer to separate Safety Data Sheet (SDS) for full handling, use and storage instructions. Keep out of reach of children. It is the user's responsibility to determine suitability for use. If in doubt, contact our Technical Department for advice.

Note: this information is for general guidance only, since site conditions and labour are beyond our control.

Dependent on the porosity of the substrate

30-50 minutes at 23°C, shorter at higher temperatures

Barcode

5060021369420

5060021369420

but as a guide 12m² per 20Kg powder

Grey powder

+5°C to +25°C

6-8 hours

2 hours

1404546

GR20-20S9-M00H-K40E

GR20-20S9-M00H-K40E

3816000000

UFI

Cement plus additives



22

13

BOND IT

H4 Premier Way, Elland. HX5 9HF. UK

EN998-1:2016

Renovation Mortar (R) for internal use.

Reaction to Fire Class F

Adhesion NPD

Release of Corrosive

Substances See MSDS



Note: The data presented in this leaflet is in accordance with the present state of our knowledge, but does not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies raw materials are also being

of investigating the possibility of infringement of third parties rights and, if necessary clarifying the position. Recommendations for use

of the fitness or suitability of the products for a





used. The recommendations do not absolve the user from the obligation

do not constitute a warranty, either expressed or implied,

particular purpose.



Size

20Kg

20Kg with mixing bucket

Part of the Bond It LevelMaster Range

Head Office: Unit H4, Premier Way, Lowfields Business Park, Elland, West Yorkshire. HX5 9HF. Telephone: +44 (0)1422 315300 Email: salesuk@bonditgroup.com

EU Office: SISL (Bond It) Ireland Limited, 70 Sir John Rogerson's Quay, Dublin 2. Tel: +353 1 960 9411 Website: www.bonditgroup.com



Version 12: Updated 07/10/24